

TECHNICAL INFORMATION SHEET

RubberGard™ MAX (Reinforced) EPDM Membrane



Item Description

1 Roll

Item Number

Various

Meets or exceeds ASTM D 4637, Type II scrim-reinforced EPDM Single-Ply roofing membranes

Product Information

Description:

Firestone RubberGard MAX (Reinforced) EPDM Membrane is an internally reinforced, cured single-ply roofing membrane that features a 9 x 9, 1,000 denier polyester weft inserted reinforcing scrim for increased puncture resistance. It is available in 0.045" (1.14 mm), 0.060" (1.52 mm) and 0.075" (1.91 mm) thicknesses. Designed with fire retardants, Firestone RubberGard MAX EPDM Membrane can meet qualification for UL Class A for slopes up to 3", depending on the roofing assembly. **NOTE:** Firestone RubberGard MAX FR Membrane is also available if higher slope classification is required.

Product Packaging

Membrane Thickness	Width	Length	Weight
0.045" (1.14 mm)	10' (3.05 m)	100' (30.5 m)	0.32 lb/ft ² (1.6 kg/m ²)
0.060" (1.52 mm)	10' (3.05 m)	100' (30.5 m)	0.42 lb/ft ² (2.1 kg/m ²)
0.075" (1.91 mm)	10' (3.05 m)	100' (30.5 m)	0.55 lb/ft ² (2.7 kg/m ²)

Rolls 10' (3.05 m) wide are no-fold panels.
Please contact your Sales or Customer Service Representative for lead time on 0.075" (1.91 mm) thick membrane.

Method of Application:

1. Substrates must be clean, dry, smooth, and free of sharp edges, fins, loose or foreign materials, oil, grease, and other materials that may damage the membrane.
2. All roughened surfaces that can damage the membrane shall be repaired as specified to offer a smooth substrate.
3. All surface voids greater than ¼" (6.3 mm) wide shall be properly filled with an acceptable fill material.
4. RubberGard MAX EPDM Membrane must be installed in accordance with current RubberGard specifications, details and workmanship requirements.

Storage:

- Store away from sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
- Store away from ignition sources as membrane will burn when exposed to open flame.

Precautions:

- Review Safety Data Sheets (SDS) prior to use.
- Take care when moving, transporting, handling, etc. to avoid sources of punctures and physical damage.
- Isolate waste products, such as petroleum products, greases, oils (mineral and vegetable) and animal fats from the RubberGard membrane.
- It is important that the side of the sheet imprinted with the direction "This Side Down" be installed in direct contact with the substrate to achieve respective test agency compliance.

TECHNICAL INFORMATION SHEET

RubberGard™ MAX (Reinforced) EPDM Membrane

LEED® Information:

Post-Consumer Recycled Content: 0%
 Post Industrial Recycled Content: 0%
 Manufacturing Location: Prescott, AR
 *NOTE: LEED® is a registered trademark of the U.S. Green Building Council.



CCMC 13265-L

Typical Properties (Meets or exceeds ASTM D 4637, Type II scrim-reinforced EPDM Single-Ply roofing membranes)

Property	ASTM Standard	Performance Minimum	Typical Performance 45 mil	Typical Performance 60 mil	Typical Performance 75 mil
Thickness, Min. Sheet - Overall	D 751	0.040" (1.016 mm)	0.043" (1.092 mm)	---	---
		0.054" (1.372 mm)	---	0.054" (1.372 mm)	---
		0.074" (1.88 mm)	---	---	0.074 (1.88 mm)
Coating Over Scrim	D 751	0.015" (0.381 mm)	0.015" (0.381 mm)	0.022" (0.559 mm)	0.029" (0.74 mm)
Breaking Strength, Min.	D 751 (Grab Method)	90 lbf (400 N)	217 lbf (965 N)	232 lbf (1032 N)	325 lbf (1446 N)
Elongation, Ultimate, Min.*	D 412 (Die C)	250%	250%	250%	250%
Tearing Strength, Min.	D 751 (Tongue Tear)	10 lbf (45 N)	60 lbf (267 N)	81 lbf (360 N)	88 lbf (391 N)
Brittleness Point, Max.	D 2137	-65 °F (-54 °C)	-65 °F (-54 °C)	-65 °F (-54 °C)	-65 °F (-54 °C)
Ozone Resistance, No Cracks	D 1149	---	Pass	Pass	Pass
Heat Aging	D 573	---	---	---	---
Breaking Strength, Min.	D 751 (Grab Method)	80 lbf (356 N)	248 lbf (1103 N)	265 lbf (1179 N)	410 lbf (1824 N)
Elongation, Ultimate, Min. ^a	D 412 (Die C)	200%	250%	250%	250%
Linear Dimensional Change, Max.:	D 1204	±1.0%	-0.7%	-0.43%	-0.43%
Water Absorption, Max., Mass %	D 471	+8%, -2 ^a %	+1.8 ^a %	+2.94 ^a %	+2.94 ^a %
Weather Resistance: Visual Inspection	D 1149	Pass	Pass	Pass	Pass
Air Permeance (Material)	E 2178**	ft ³ /ft ² (L/(s·m ²))	<0.004 (0.02)	Pass	Pass

*Specimens to be prepared from coating rubber compound, vulcanized in a similar method to the reinforced products.

**The ASTM 2178 values listed are for the air permeance of the UltraPly TPO Membrane component only. For use of the product as a component in an air barrier assembly, please consult your Firestone Technical Advisor, Code Agency or Authority having Jurisdiction (AHJ) for the acceptable air barrier assembly details.

Please contact Firestone Technical Services Department at 1-800-428-4511 for further information.

This sheet is meant to highlight Firestone products and specifications and is subject to change without notice. Firestone takes responsibility for furnishing quality materials which meet published Firestone product specifications. Neither Firestone nor its representatives practice architecture. Firestone offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. Firestone accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Firestone representative is authorized to vary this disclaimer.