

TECHNICAL INFORMATION SHEET

RubberGard™ Max FR (Fire Retardant) EPDM Membrane

Item Description

45-mil 10' X 100'
60-mil 10' X 100'

Item Number

W57SF41010
W57SF61010



Product Information

Description:

Firestone RubberGard MAX FR EPDM is an internally reinforced, cured single-ply roofing membrane that features 9 x 9, 1,000 denier polyester weft inserted scrim reinforcement for increased puncture resistance. Designed with fire retardants, Firestone RubberGard MAX FR Membrane can meet qualification for unlimited UL Class A slope, depending on the roofing assembly.

Preparation of Substrate:

1. Substrates must be clean, dry, smooth, and free of sharp edges, fins, loose or foreign materials, oil, grease, and other materials that may damage the membrane.
2. All roughened surfaces that can damage the membrane shall be repaired as specified to offer a smooth substrate.
3. All surface voids greater than ¼" (6.3 mm) wide shall be properly filled with an acceptable fill material.

Method of Application:

RubberGard MAX FR EPDM Membrane must be installed in accordance with current RubberGard specifications, details and workmanship requirements.

Storage:

- Store away from sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
- Store away from ignition sources as membrane will burn when exposed to open flame.

Precautions:

- Take care when moving, transporting, handling, etc. to avoid sources of punctures and physical damage.
- Assure that structural decking will support the loads incurred by material when stored on rooftop. The deck load limitations should be specified by the project designer.
- Isolate waste products, such as petroleum products, greases, oils (mineral and vegetable) and animal fats from the RubberGard membrane.
- Refer to Safety Data Sheets (SDS) for safety information.

LEED® Information:

Post-Consumer Recycled Content: 0%
Post Industrial Recycled Content: 0%
Manufacturing Location: Prescott, AR

*NOTE: LEED® is a registered trademark of the U.S. Green Building Council.



TECHNICAL INFORMATION SHEET

RubberGard™ Max FR (Fire Retardant) EPDM Membrane

Packaging:

.045" MAX FR : 10' (3 m) x 100' (30.5 m) - 0.32 lb/sf (1.5 kg/m²)

.060" MAX FR: 10' (3 m) x 100' (30.5 m) - 0.42 lb/sf (2.1 kg/m²)

NOTE: Available sizes vary by product. Contact Firestone Customer Service for availability and packaging information.

Typical Properties

| Property | ASTM Standard | Units | Performance Minimum | Typical Values 45-mil | Typical Values 60-mil |
|-------------------------------------------|--------------------------------|----------------------------------------------------------|----------------------------------|--------------------------------|-----------------------|
| Thickness, minimum Sheet-overall | D751 | inch (mm) | 0.0405 (1.016) 0.0504 (1.372) | 0.043 (1.092) | 0.059 (1.499) |
| Coating over Scrim | D751 | inch (mm) | 0.015 (0.381) | 0.015 (0.381) | 0.022 (1005) |
| Breaking Strength, minimum | D751 Grab Method | Lbf(N) | 90 (400) | 240 (1068) | 226 (1005) |
| Elongation, Ultimate, minimum | D412 Die C | % | 250 ^a | 400 ^a | - |
| Tensile Strength, minimum | D751 Tongue Tear | Lbf(N) | 10 (45) | 60 (267) | 79 (351) |
| Brittleness Point, maximum | D2137 | ° F (° C) | -49 (-45) | -65 (-54) | -49 (-45) |
| Ozone Resistance, no cracks | D1149 | - | - | Pass | Pass |
| Heat Aging: Breaking Strength, minimum | D573 | - | - | - | - |
| Elongation, ultimate, minimum | D751 Grab Method D412 Die C | Lbf(N) % | 80(356) 200 ^a | 275 (1223) 300 ^a | 284 (1263) - |
| Linear Dimensional change, maximum | D1204 | % | ±1.0 | -0.7 | -.37 |
| Water Absorption, maximum, mass % | D471 | % | +8,-2 ^a | +1.8 ^a | +2.64 ^a |
| Weather Resistance: Visual Inspection | D518 | - | Pass | Pass | Pass |
| Air Permeance (Material) | E2178* | ft ³ /ft ² (L/(s·m ²)) | <0.004 (0.02)) | Pass | Pass |

*The ASTM 2178 values listed are for the air permeance of the UltraPly TPO Membrane component only. For use of the product as a component in an air barrier assembly, please consult your Firestone Technical Advisor, Code Agency or Authority having Jurisdiction (AHJ) for the acceptable air barrier assembly details.



Please contact Firestone Technical Services Department at 1-800-428-4511 for further information.

This sheet is meant to highlight Firestone products and specifications and is subject to change without notice. Firestone takes responsibility for furnishing quality materials which meet published Firestone product specifications or other technical documents, subject to normal roof manufacturing tolerances. Neither Firestone nor its representatives practice architecture. Firestone offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. Firestone accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Firestone representative is authorized to vary this disclaimer.